


Grade	C	Si	Mn	P	S	N	Al	Cu	Cr	Mo	Ti	V	Nb	Mo
S115 (EN10 130)	0.024	0.008	0.195	0.005	0.006	0.0047	0.003	0.006	0.014	0.0032	0.001	0.001	0	0.002
S115 (5min 500°C)	0.027	0.009	0.204	0.007	0.008	0.0058	0.011	0.009	0.013	0.040	0.001	0.002	0.001	0.002
ZS1E2201 (5min 500°C)	0.023	0.013	0.188	0.005	0.005	0.0038	0.016	0.021	0.022	0.013	0.019	0.001	0	0.004
ZS1E2201 (700°C)	0.023	0.011	0.188	0.011	0.005	0.0048	0.017	0.011	0.021	0.003	0.021	0.001	0	0.004
ZS1E2201 (500-40)	0.016	0.018	0.173	0.011	0.002	0.0022	0.016	0.021	0.023	0.002	0.017	0.001	0.001	0.002

Table 1: Chemical composition

Steel grade	Yield strength MPa	Tensile strength MPa	Elongation to fracture	BH <sub>1</sub> MPa
S115 (EN10 130)	up to 180	270 to 390	at least 40	-
S115 (5min 500°C)	150	300	35	at least 38
S115 (2min 700°C)	180	380	30	at least 58
ZS1E2201 (SZAG W5/94)	from 220	300 to 380	at least 36	-
ZS1E2201 (5min 500°C)	220	340	34	at least 41
ZS1E2201 (2min 700°C)	250	380	28	at least 80
ZS1E240 (SEW058)	340 to 440	410 to 530	at least 20	-
ZS1E240 (5min 600°C)	380	470	22	at least 18
ZS1E240 (2min 700°C)	390	480	20	at least 35
ZS1E2201H (SEW064)	220 to 280	320 to 400	at least 30	from 40

Table 2

United States Patent & Trademark Office  
Office of Initial Patent Examination — Scanning Division



Application deficiencies found during scanning:

☐ Page(s) \_\_\_\_\_ of \_\_\_\_\_ were not present  
for scanning. (Document title)

☐ Page(s) \_\_\_\_\_ of \_\_\_\_\_ were not present  
for scanning. (Document title)

☐ *Scanned copy is best available.*

*Some specification pages have lines in through them.*